

MP100
Metal Primer
DESCRIPTION

SCIGRIP® MP100 Metal Primer is a surface treatment that is designed to clean, chemically convert and prepare stainless steel and aluminum surfaces¹ for permanent bonding with SCIGRIP Methacrylate Structural Adhesives. It significantly improves the long-term durability of adhesive bonds that are subjected to humid or corrosive environments such as salt water or salt spray. Without MP100, certain SCIGRIP Structural Series Adhesives can lose bond strength over time when exposed to such conditions.

MP100 Metal Primer is recommended with SG100, SG200, SG230 HV, SG600, SG745 and SG747 for metal bonding. The SG300 and SG5000 do not require use of primer. A thin film of the metal primer is brushed or wiped on metal surfaces and allowed to dry completely before application of adhesive.

MP100 Metal Primer is packaged in 1 pint (473 ml) bottles.

APPLICATION

MP100 Metal Primer is applied by simply brushing or wiping on metal surfaces prior to application of adhesive. For best results use only thin coats of the primer and allow the primer to dry completely prior to application of adhesive.

PERFORMANCE BENEFITS

• Simple brush or wipe application, rapid dry	➔	Minimal added time and labor input
• Mild solvent action	➔	Cleans metal surface prior to conversion
• Aggressive etching & chemical conversion	➔	Reduces surface corrosion & chemically links adhesive to metal surface
• Red color	➔	Simplifies application, facilitates visual inspection

TYPICAL ADHESIVE CHARACTERISTICS @ 75°F (24°C)

Physical Form	Water-thin liquid solution
Color	Red
Density, g/cc	0.78
Density, lb/gallon	6.50
Shelf life	One Year ²
Dry Time	Fast drying (5 to 10 minutes at ambient temperatures)

NOTES:

1. Contact manufacturer for test data on specific metal substrates.
2. See "Storage and Shelf Life" on back page.

SAFETY AND HANDLING

Read Material Safety Data Sheet before handling or using this product. MP100 Metal Primer is flammable. Always use in a well-ventilated area. Floor-level extraction and large quantities of moving air greatly facilitate ventilation. MP100 should be stored in a cool place away from sources of heat and open flames or sparks. Keep container closed when not in use. Prevent contact with skin and eyes. In case of skin contact, wash with soap and water. In case of eye contact, flush with water for 15 minutes and seek immediate medical attention. Harmful if swallowed. Keep out of reach of children.

APPLICATION

Remove excess surface contaminants such as dust, grime, grease or oil by washing or wiping with a clean cloth. Surface should be dry before applying primer. Apply a thin coat of primer by brushing, wiping or dipping. Avoid forming puddles or heavy layers of primer. Remove excess primer by wiping while still wet, or remove with a clean rag dampened with alcohol. Re-apply if necessary to provide a thin, uniform layer.

SHELF LIFE & STORAGE CONDITIONS:

The shelf life of MP100 Metal Primer in unopened containers is twelve (12) months from the date of shipment to you from IPS Adhesives unless otherwise explicitly stated. Shelf life is based on a continuous, steady state storage temperature of between 65°F (18°C) and 80°F (27°C). Exposure to temperatures below 65°F (18°C) or above 80°F (27°C) will impact the product performance and viscosity. Exposure to temperatures above 80°F (27°C) will rapidly reduce the stated shelf life of the product.

PRODUCT APPLICATION & USE:

To ensure consistent performance, product temperatures must be held reasonably constant between 65°F (18°C) and 80°F (27°C). Substrate preparation, adhesive/activator ratio, application temperature, humidity and a variety of other environmental and end user application factors are beyond the control of IPS Adhesives; therefore, the end user is solely responsible for determining whether the product is fit for a specific purpose and suitable for the user's product, design and final application requirements.

IMPORTANT NOTES

- a. **SUBSTRATE AND APPLICATION COMPATIBILITY.** The user must determine the suitability of a selected adhesive for a given substrate and application. SCIGRIP strongly recommends laboratory, shop and end-use testing that simulates the actual manufacturing and end-use environment.
- b. **SURFACE PREPARATION.** The need for surface preparation must be determined by comparative testing of prepared and unprepared substrates to assure that unprepared bonding is equivalent to or acceptable for the application relative to prepared bonding. Initial bonding tests must be followed up with simulated or actual durability tests to assure that surface conditions do not lead to degradation of the bond over time under service conditions. Subsequent changes in substrates or bonding conditions will require re-testing.
- c. **TECHNICAL ASSISTANCE.** Contact your SCIGRIP representative for questions or assistance with the selection of adhesives and methods for evaluating adhesives for your intended application.

NOTE: *This product is intended for use by skilled individuals at their own risk. Recommendations contained herein are based on information we believe to be reliable. The properties and strength values presented above are typical properties obtained under controlled conditions at the SCIGRIP laboratory. They are intended to be used only as a guide for selection for end-use evaluation. The ultimate suitability for any intended application must be verified by the end user under anticipated test conditions. Since specific use, materials and product handling are not controlled by SCIGRIP, our warranty is limited to the replacement of defective SCIGRIP products.*

Limited Warranty: **Seller warrants to the original Buyer of the goods that all new Seller goods shall be free from defects in material and workmanship for the published shelf life of the good. If any Seller good fails to conform to this Limited Warranty under normal use and storage conditions, and if the original Buyer complies with the terms of this Limited Warranty, then Seller will, without charge to Buyer, replace the nonconforming good.**

This Limited Warranty shall not extend to, nor shall Seller be responsible for, damages or loss resulting from accident, misuse, negligent use, improper storage, or improper application.

THIS LIMITED WARRANTY IS EXCLUSIVE AND IN LIEU OF ALL OTHER WARRANTIES. SELLER MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, EITHER IN FACT OR BY OPERATION OF LAW, STATUTORY OR OTHERWISE, AND EXPRESSLY DISCLAIMS ANY WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, ARISING FROM A COURSE OF DEALINGS, AND/ OR FROM USAGE OF TRADE.

SELLER SHALL NOT BE LIABLE IN CONTRACT, IN TORT (INCLUDING NEGLIGENCE OR STRICT LIABILITY) OR OTHERWISE FOR ANY SPECIAL, INDIRECT, INCIDENTAL, PUNITIVE OR CONSEQUENTIAL DAMAGES.